

#### EKOTEKS LABORATUVAR ve GÖZETİM HİZMETLERİ A.Ş.

Esenyurt Firuzköy Bulvarı No:29 34325 Avcılar İstanbul/ TÜRKİYE





AB-0583-T 21020673

07-21

Customer name:

ARITEKS BOYACILIK TİCARET VE SAN. AŞ.

Address:

VELİ<mark>M</mark>EŞE OSB. MAH. HACI ŞEREMET SOKAK 9/9 ERGENE/TEKİRDAĞ

Buyer name:

Contact Person:

ÖZGÜR KUŞKU

Order No:

Article No:

ArShirt-3938, Navy

Name and identity of test item:

Navy blue knitted fabric.

The date of receipt of test item:

28.06.2021

Re-submitted/re-confirmation

date:

28.06.2021-02.07.2021

Remarks:

Sampling:

Date of test:

The results given in this report belong to the received sample by vendor.

End-Use:

Care Label:

Not Specified

Number of pages of the report:

The Turkish Accreditation Agency (TURKAK) is signatory to the multilateral agreements of the European co-operation for the Accreditation (EA) and of the International Laboratory Accreditation (ILAC) for the Mutual recognition of test

EKOTEKS LABORATUVAR ve GÖZETİM HİZMETLERİ A.Ş. accredited by TÜRKAK under registration number [AB-0583-T] for ISO 17025:2017 as test laboratory.

The test and/or measurement results, the uncertainties (if applicable) with confidence probability and test methods are given on the following pages which are part of this report.

Seal

Date 02.07.2021 Customer Repre

Head of Testing Laboratory Sevim A. RAZA 02.07.202


This report shall not be reproduced other than in full except with the permission of the laboratory. Testing reports without signature and seal are not valid.

#### EKOTEKS LABORATUVAR ve GÖZETİM HİZMETLERİ A.Ş.

AB-0583-T 21020673 07-21

REQUIRED TESTS	RESULT	COMMENTS
COLOR FASTNESS TESTS		
Color Fastness to Perspiration	-	

**REMARK:** Original samples are kept for 3 months and all technical records are kept for 5 years unless otherwise specified. If requested, measurement uncertainty will be reported. But unless otherwise specified, measurement uncertainty is not considered while stating compliance with specification or limit values. The reported uncertainty is based on a standard uncertainty multiplied by a coverage factor k=2, providing a level of confidence of approximately 95 %. The declaration of conformity was given in accordance with the Simple Acceptance Decision Rule. Tests marked (\*) in this report are not included in the accreditation schedule.



This report shall not be reproduced other than in full except with the permission of the laboratory. *Testing reports without signature and seal are not valid* 

### EKOTEKS LABORATUVAR ve GÖZETİM HİZMETLERİ A.Ş.

AB-0583-T 21020673 07-21

## **TEST RESULT**

# COLOURFASTNESS TO PERSPIRATION; ISO 105 E04:2013

37±2°C@4 hours. DW multifiber. Perspirometer. Evaulated with ISO 105 A02 and ISO 105 A03 standart grey scale

Colour Change	RESULT				REQUIREMENT		
Acidic		4-5					-
Alkaline			4-5				
Staining	Asstata	Catton	Nylon 6.6	Polyester	Acrylic	Wool	
Acidic	Acetate 4-5	Cotton 4-5	4-5	4-5	4-5	4-5	
Alkaline	4-5	4-5	4-5	4-5	4-5	4-5	•

	COLOUR FASTNESS RATING		
	COLOUR CHANGE		COLOUR STAINING
5	Negligible or no change	5	Negligible or no staining
4	Slightly changed	4	Slightly stained
3	Noticeably changed	3	Noticeably stained
2	Considerably changed	2	Considerably stained
1	Much changed	1	Much stained