

AB-0583-T

21010380

04-21

Customer name: ARITEKS BOYACILIK TİCARET VE SAN. A.Ş.
Address: Hacı Şeremet 5. Sok. 59850 YULAFLI/ ÇORLU/ TEKİRDAĞ
Buyer name: -
Contact Person: ÖZGÜR KUŞKU
Order No: 2
Article No: ArGün 260 – 6077 – Black
Name and identity of test item: One sample of black woven fabric.
The date of receipt of test item: 23.03.2021
Re-submitted/re-confirmation date: 06.04.2021
Date of test: 06.03.2021 – 08.04.2021
Remarks: -
Sampling: The results given in this report belong to the received sample by vendor.
End-Use: -
Care Label: Not specified.

Number of pages of the report: 3

The Turkish Accreditation Agency (TURKAK) is signatory to the multilateral agreements of the European co-operation for the Accreditation (EA) and of the International Laboratory Accreditation (ILAC) for the Mutual recognition of test reports.

EKOTEKS LABORATUVAR ve GÖZETİM HİZMETLERİ A.Ş. accredited by TÜRKAK under registration number [AB-0583-T] for ISO 17025:2017 as test laboratory.

The test and/or measurement results, the uncertainties (if applicable) with confidence probability and test methods are given on the following pages which are part of this report.



Date
08.04.2021

Customer Representative
Özlem UYSAL

Head of Testing Laboratory
Sevim A. RAZAK

08.04.2021

This report shall not be reproduced other than in full except with the permission of the laboratory.
Testing reports without signature and seal are not valid.

EKOTEKS LABORATUVAR ve GÖZETİM
HİZMETLERİ A.Ş.


AB-0583-T

21010380

04-21

REQUIRED TESTS	RESULT	COMMENTS
COLOR FASTNESS TEST		
Colourfastness to perspiration	-	
No requirement was given by vendor.		

REMARK: Original samples are kept for 3 months and all technical records are kept for 5 years unless otherwise specified. If requested, measurement uncertainty will be reported. But unless otherwise specified, measurement uncertainty is not considered while stating compliance with specification or limit values. The reported uncertainty is based on a standard uncertainty multiplied by a coverage factor $k=2$, providing a level of confidence of approximately 95 %. The declaration of conformity was given in accordance with the Simple Acceptance Decision Rule. Tests marked (*) in this report are not included in the accreditation schedule.



Gen.fl136-2/03

This report shall not be reproduced other than in full except with the permission of the laboratory.
Testing reports without signature and seal are not valid.

EKOTEKS LABORATUVAR ve GÖZETİM
HİZMETLERİ A.Ş.

AB-0583-T

21010380

04-21

TEST RESULTS

COLOURFASTNESS TO PERSPIRATION; ISO 105 E04:2013

37±2°C@4 hours. DW multifiber

Evaluated with ISO 105 A02 and ISO 105 A03 standart grey scale

Colour Change							<u>RESULT</u>	<u>REQUIREMENT</u>
Acidic							4-5	-
Alkaline							4-5	-
Staining	Acetate	Cotton	Nylon 6.6	Polyester	Acrylic	Wool		
Acidic	4-5	4-5	4-5	4-5	4-5	4-5	-	
Alkaline	4-5	4-5	4-5	4-5	4-5	4-5	-	

Gen.fl136-2/03

COLOUR FASTNESS RATING

COLOUR CHANGE

5	Negligible or no change
4	Slightly changed
3	Noticeably changed
2	Considerably changed
1	Much changed

COLOUR STAINING

5	Negligible or no staining
4	Slightly stained
3	Noticeably stained
2	Considerably stained
1	Much stained