



EKOTEKS

TÜRKAK
TÜRK AKREDİTASYON KURUMU
TURKISH ACCREDITATION AGENCY
tarafından akredite edilmiş



Test
TS EN ISO/IEC 17025
AB-0583-T

EKOTEKS LABORATUVAR ve GÖZETİM
HİZMETLERİ A.Ş.

Esenyurt Firuzköy Bulvarı No:29 34325 Avcılar
İstanbul/ TÜRKİYE

TEST REPORT
DENEY RAPORU

AB-0583-T

16013051

03-16

Customer name: ARITEKS BOYACILIK TİCARET VE SAN. A.Ş.
Address: Velimeşe OSB Mah. Hacı Şeremet 5. Sokak 9/9 ERGENE/ TEKİRDAĞ
Buyer name: -
Contact Person: ÖZGÜR KUŞKU
Order No: -
Article No: -
Name and identity of test item: One sample of (claimed to be 100% PES Warp Knitted Navy Color Fabric; ArNeo Color Navy) navy knit fabric.
The date of receipt of test item: 18.03.2016
Re-submitted/re-confirmation date: 22.03.2016
Date of test: 22.03.2016-25.03.2016
Remarks: -
Sampling: The results given in this report belong to the received sample by vendor.
End-Use: -
Care Label: Not specified.
Number of pages of the report: 3

The Turkish Accreditation Agency (TURKAK) is signatory to the multilateral agreements of the European co-operation for the Accreditation (EA) and of the International Laboratory Accreditation (ILAC) for the Mutual recognition of test reports.

The test and/or measurement results, the uncertainties (if applicable) with confidence probability and test methods are given on the following pages which are part of this report.

Seal

Date
25.03.2016

Customer Representative
N. Fisun EROL

Head of Testing Laboratory
Sevim A. RAZAK

This report shall not be reproduced other than in full except with the permission of the laboratory.
Testing reports without signature and seal are not valid.

**EKOTEKS LABORATUVAR ve GÖZETİM
HİZMETLERİ A.Ş.**

AB-0583-T
16013051
03-16

REQUIRED TESTS	RESULT	COMMENTS
PHYSICAL PROPERTIES TESTS		
Bursting Strength	-	
No requirement was given by vendor.		

REMARK: Original samples are kept for 3 months and all technical records are kept for 5 years unless otherwise specified. The reported uncertainty is based on a standard uncertainty multiplied by a coverage factor $k=2$, providing a level of confidence of approximately 95 %. Tests marked (*) in this report are not included in the accreditation schedule.



This report shall not be reproduced other than in full except with the permission of the laboratory.
Testing reports without signature and seal are not valid.

**EKOTEKS LABORATUVAR ve GÖZETİM
HİZMETLERİ A.Ş.**

AB-0583-T
16013051
03-16

TEST RESULTS

BURSTING STRENGTH; ISO 13938-1:1999

SDL ATLAS M229 tester. Test area: 30.5 mm diameter

Rate of increase in volume; 129.1 cm³/min.

The average results are given of five samples.

Performed in the conditioned room (20±2°C-65%±4).

	<u>RESULT</u>	<u>REQUIREMENT</u>
	1290.7 kPa	-
Height at Burst*	11.4 mm	